



BRISA DISTRESSED

APPLICATIONS

Interior Upholstery

GENERAL SPECIFICATIONS

Composition:

100% Polycarbonate Polyurethane Surface
65% Recycled Polyester, 35% Rayon Backing

Weight:

Approx. 8.9 oz. Per Square Yard

Approx. 300 Grams Per Square Metre

Thickness:

Approx. 0.95 Millimetres

Width:

54 Inches / 137 Centimetres

Repeat:

8"V x 10.5"H / 203mm V x 267mm H

PERFORMANCE

Abrasion:

ASTM D4157 / 300,000 Double Rubs (Wyzenbeek)*

BS EN ISO 12947-2 / 160,000 Rubs (Martindale)*

*meets or exceeds

Hydrolysis:

16 Weeks

ASTM D3690 Sect. 6.11 (Hydrolytic Stability)

ISO 1419 Method C (Accelerated Ageing)

Adhesion of Coating: ASTM D751

Tear Strength: ASTM D2261

Breaking Strength: ASTM D751

Tensile Strength: BS EN ISO 1421

Air Permeability: ASTM D737

Sound Absorption: ASTM C423

COLORFASTNESS

Light: AATCC 16.3, 200 Hours, Grade 4

ISO 105 B02, Grade 6

Crocking: AATCC 8, Grade 4-5 Wet & Dry

FLAMMABILITY REQUIREMENTS

· ASTM E84 (Adhered) - Class A

· CA TB 117-2013 - Pass

· FMVSS 302 - Pass

· NFPA 260 - Class 1

· UFAC - Class 1

These fabrics, when treated and/or used with other compatible furniture components, have been shown to perform under the fire test conditions of:

· ASTM E84 (Unadhered)

· BS 5852 Source 0, 1 & 5

· IMO FTPC Part 8

(Cig, Match & Crib 5)

· BS EN 1021 Parts 1 & 2

* Only in North America

CLEANING INSTRUCTIONS

One of the best ways to keep Ultrafabrics looking great is through proper maintenance and regular cleaning to prevent excessive dirt from accumulating. To help keep your quality fabrics looking their best, follow these guidelines to extend the life of the fabric:

- Wipe up spills as soon as they occur

- Clean with soap and water

- Sanitize using disinfectants such as (1:5) bleach/water solution

- For stubborn stains, wipe off with isopropyl alcohol as soon as possible*

- Thoroughly rinse all solution residue with clean water

- Air dry

This information is not a guarantee. Please use all cleaning and disinfecting agents safely and as instructed.